



## **RED CONCRETE TINTING MATERIAL FIELD SECTION 1056**

**1056.1 Scope.** To establish procedures for sampling red tinting material for use in portland cement concrete.

**1056.2 Apparatus.**

- (a) Appropriate sampling thief.
- (b) One-half inch [12 mm] sample splitter.

**1056.3 Procedure.** Care shall be exercised in obtaining the sample because the material is subject to segregation. At least three bags should be selected and a sample obtained from each bag by use of an appropriate sampling thief. The sample shall be reduced to approximately one quart [1 liter] by use of a one inch [25 mm] sample splitter, taking care to eliminate loss of tinting compound during the splitting procedure. The sample shall be submitted to the Laboratory in a one quart [1 liter] friction top can accompanied by a properly completed Form T-617 showing the manufacturer's name, the brand name and designation of the material, lot number, and net quantity represented.